
Nitrile Examination Glove (3.0g)



| Product specifications | | | | |
|---|---|---|---------------------------|--|
| Туре | Nitrile Exam | ination Glove, Powder Free, | Non-sterile, Ambidextrous | |
| Product code | NBR02/ NBF | NBR02/ NBR04 | | |
| Material: | 100% Synth | 100% Synthetic Nitrile Latex | | |
| Color: | | Blue/white/Purple | | |
| Classification | Class 1 | | | |
| Sizes: | X-Small, Sm | X-Small, Small, Medium, Large, X-Large | | |
| Surface Finishing | Full Texture | Full Textured or Finger Textured, Chlorinated or Polymer Coated | | |
| Cuff | Beaded | | | |
| Protein content | NA | NA | | |
| Standard: | ASTM D631 | ASTM D6319 | | |
| Application: | | Examination, Food Handling, Laboratory, Sanitary Protection, Beauty | | |
| Storage | Industry, Etc. Cool & Dry Place with temperature not higher than 30°C. | | | |
| Shelf-life | | 5 years from date of manufacturing | | |
| Physical Dimensions | , | | | |
| | | Standards | | |
| Dimensions | | Tradecyanic | ASTM 6319 | |
| Length (mm) | | 240 min | 230 ±10 | |
| Width (mm) | | | | |
| Extra-small | | 75±5 | 70±10 | |
| Small | | 85±5 | 80±10 | |
| Medium | | 95±5 | 95±10 | |
| Large | | 105±5 | 110±10 | |
| Extra-large | | 115±5 | 120±10 | |
| Thickness (mm) | | | | |
| Fingers (13 mm from fingertip) | | 0.08 min | 0.05 min | |
| Palm (center of palm) | | 0.06 min | 0.05 min | |
| | Cuff (25 mm from the bead) | | - | |
| Cuff (25 mm from the beau | , , , , , , , , , , , , , , , , , , , | | | |
| | <i>,</i> | | | |
| Average Weight± 0.2 g | 4 J | 2.2g | | |
| Average Weight± 0.2 g Extra-small | , , | • | | |
| Average Weight± 0.2 g Extra-small Small | × | 2.5g | | |
| Cuff (25 mm from the beau Average Weight± 0.2 g Extra-small Small Medium Large | × | • | | |

| Physical Properties | | | |
|--|-------------|---------|--|
| Property | TRADECYANIC | ASTM | |
| Force at Break Before Aging (EN455-2) | ≥ 6 N | ≥ 6 N | |
| Force at Break After Aging (EN455-2) | ≥ 6 N | ≥ 6 N | |
| Tensile Strength Before Aging (ASTM D6319) | ≥14 MPa | ≥14 MPa | |
| Tensile Strength After Aging (ASTM D6319) | ≥14 MPa | ≥14 MPa | |
| Elongation Before Aging (ASTM D6319) | ≥ 500% | ≥ 500% | |
| Elongation After Aging (ASTM D6319) | ≥ 400% | ≥ 400% | |

According to the measure by ASTM D412, Standard Test Methods for Vulcanized Rubber and Thermoplastic Elastomers – Tension. Aged according to ASTM D573, Standard Test Method for Rubber – Deterioration in an Air Oven

| Pre-shipment Inspection Sampling | | | | |
|----------------------------------|------------------|-----|--|--|
| Criteria | Inspection Level | AQL | | |
| Dimensions & Thickness | S2 | 4.0 | | |
| Physical properties | S2 | 4.0 | | |
| Water Tight Test (Palm) | G1 | 2.5 | | |
| Major visual defect | G1 | 2.5 | | |
| Minor visual defect | G1 | 4.0 | | |

AQL levels defined according to ISO 2859-1 for sampling by attributes.

| Standard Packing | | | | |
|----------------------------|---|--|--|--|
| Fully Packed | 100 gloves by weight per box, 10 boxes per carton | | | |
| Bulk Pack | As specified by customer | | | |
| Quantity 20Ft container | 1900 cartons according to our carton | | | |
| Quantity 40Ft HQ container | 4720 cartons according to our carton | | | |